



# 24451 Flexo InkJet Receptive Clear

Polymeric's 24451 Flexo InkJet Receptive Clear is specifically designed to be used on holographic film.

## **Anilox**

800LA 1.8 BCM

## **Material**

Holographic Polyester film-*no corona treatment necessary*

## **Cure Parameters**

1-500 watt per inch medium pressure mercury vapor lamp with 150-180 mJ at 165 fpm

## **Approved Presses**

Domino 610 UV Inkjet Printer

## **Mixing**

The 24451 Flexo InkJet Receptive Clear is supplied at print-ready viscosity and can be used directly from the container. Thinning is not recommended.

## **Storage**

Care should be taken to store ink in tightly closed containers located in a cool (60-80°F/15-27°C) dark place. With suitable conditions, unopened ink is expected to have a shelf life of approximately twelve (12) months from date of manufacture, six (6) months for white inks.

## **Precautions**

Read the safety data sheet prior to processing. It contains instructions for precautions to be taken when handling inks. If ink comes in contact with skin wipe off with a clean, dry cloth (do not use solvent). Wash and rinse the affected areas with soap and water.

Polymeric's Ink Jet Receptive Clear has been qualified on the Domino 610 ink jet printer. The 24451 may work on a variety of plastics but should be thoroughly pretested prior to actual production run. Specifically designed for UV ink jet printers, it is not intended for use with dye or water-based systems.

### **A. Warranty Liability Limited to Purchase and Installation Costs**

Notwithstanding anything provided herein or any other written material to the contrary, Polymeric only warrants the purchase price and costs of installation. Polymeric US shall have no liability or obligation to any user, buyer, purchaser, distributor or other person or entity for any special, direct, indirect, incidental or consequential damages, however caused, including without limitation, personal liability, loss of business, loss of profit, or other damage, whether or not buyer shall have informed Polymeric US of the possibility or likelihood of any such damages.

### **B. Limitation of Implied Warranty and Fitness for a Particular Purpose**

Polymeric's warranty is given in lieu of all other warranties, express or implied, including but not limited to an implied warranty of fitness for a particular purpose, an implied warranty of merchantability, and any other implied warranty arising out of a course of dealing, performance, customer usage or trade.

### **C. A Pretest Prior to Production is Recommended to Ensure Proper Suitability for the Intended Application.**